

## Rubber sheet Neoprene

GOVT.RECOGNISED EXPORT HOUSE				
TECHNICAL SPECIFICATIONS				
QUALITY : COMMERCIAL NEOPRENE RUBBER CODE: NE 7010				
PROPERTIES	TEST METHOD	VALUES	TEST METHOD	VALUE
		FPS UNITS		METRIC UNITS
SPECIFIC GRAVITY	DIN 53508	1.45 ± 0.05	ASTM D297	1.45 ± 0.05
HARDNESS	DIN 53505	65 ± 5 Sh A	ASTM D2240	65 ± 5 Sh A
TENSILE STRENGTH ( min )	DIN 53504	569 PSI	ASTM D412	40 kg/cm <sup>2</sup>
ELONGATION AT BREAK ( min )	DIN 53504	200%	ASTM D412	200%
COMPRESSION SET (70 °C/24 hrs/25% set) (max)	DIN ISO 815-1	40%	ASTM D395 METHOD B	40%
TEAR RESISTANCE ( Angular ) min	DIN 53515	100 Lbs/Inch	ASTM D624	18 Kg/cm
CHANGE IN PROPERTIES				
HEAT AGEING ( 72 hrs. AT 70 °C )			ASTM D573	
--- HARDNESS (Pts)		+ 5 (Max)		+ 5 (Max)
--- TENSILE STRENGTH (%)		+ 10 / - 25		+ 10 / - 25
--- ELONGATION AT BREAK (%)		+ 10 / - 25		+ 10 / - 25
VOLUME SWELL : AT 70° C FOR 72 HRS/IN			ASTM D 471	
IRM OIL NO.1		+ 33%		+ 33%
IRM OIL NO.2		+ 47%		+ 47%
IRM OIL NO.3		+ 90%		+ 90%
<b>POLYMER CONTENT (NEOPRENE)</b>		10%		10%
<b>CHEMICAL RESISTANCE</b>				
--- OZONE		FAIR	ASTM D 1149	FAIR
--- DILUTE ACIDS AND BASES		FAIR		FAIR
--- CONCENTRATED ACIDS AND BASES		NOT RECOMMENDED		NOT RECOMMENDED
--- OILS		NOT RECOMMENDED		NOT RECOMMENDED
--- SOLVENTS		NOT RECOMMENDED		NOT RECOMMENDED
TEMPERATURE RANGE		-30 ° to +90° C		-30 ° to +90° C
COLOUR		BLACK		BLACK